



**SHERWIN
WILLIAMS.**

SherLux Harmony Semi Gloss

Description	System Recommendation																														
<p>SherLux Harmony Semi Gloss is an excellent, durable quality low odor zero voc interior 100 % Acrylic Semi Gloss paint which is having good, washability hiding, whiteness, luxury finish and leveling properties .Excellent adhesion to the substrate. Anti – Microbial and Anti Bacterial properties. Wide range of vibrant colors.</p>	<p>On old & Porous Substaries:</p> <table border="1"> <tr> <td>SherLux Base Coat</td> <td>One coat to fill imperfections</td> </tr> <tr> <td>SherLux Prep Masonry Primer</td> <td>One coat</td> </tr> <tr> <td>SherLux Harmony Semi Gloss</td> <td>Two Coats</td> </tr> </table> <p>On new cured concrete, plastered and gypsum substrates:</p> <table border="1"> <tr> <td>SherLux Base Coat</td> <td>One coat to fill imperfections</td> </tr> <tr> <td>SherLux Prep Masonry Primer</td> <td>One coat</td> </tr> <tr> <td>SherLux Harmony Semi Gloss</td> <td>2 Coats</td> </tr> </table> <p>Drying Time: Typically at recommended film thickness , drying time is generally depend on good ventilation.</p> <table border="1"> <thead> <tr> <th rowspan="2">Substrate</th> <th rowspan="2">Dry to Touch</th> <th rowspan="2">Dry to Handle</th> <th colspan="2">Re-coating Interval</th> </tr> <tr> <th>Minimum</th> <th>Maximum</th> </tr> </thead> <tbody> <tr> <td>23° C</td> <td>30 mnts</td> <td>3 h</td> <td>2hr</td> <td></td> </tr> <tr> <td>35° C</td> <td>15 mnts</td> <td>2 h</td> <td>1hr</td> <td></td> </tr> </tbody> </table>		SherLux Base Coat	One coat to fill imperfections	SherLux Prep Masonry Primer	One coat	SherLux Harmony Semi Gloss	Two Coats	SherLux Base Coat	One coat to fill imperfections	SherLux Prep Masonry Primer	One coat	SherLux Harmony Semi Gloss	2 Coats	Substrate	Dry to Touch	Dry to Handle	Re-coating Interval		Minimum	Maximum	23° C	30 mnts	3 h	2hr		35° C	15 mnts	2 h	1hr	
SherLux Base Coat	One coat to fill imperfections																														
SherLux Prep Masonry Primer	One coat																														
SherLux Harmony Semi Gloss	Two Coats																														
SherLux Base Coat	One coat to fill imperfections																														
SherLux Prep Masonry Primer	One coat																														
SherLux Harmony Semi Gloss	2 Coats																														
Substrate	Dry to Touch	Dry to Handle	Re-coating Interval																												
			Minimum	Maximum																											
23° C	30 mnts	3 h	2hr																												
35° C	15 mnts	2 h	1hr																												
Characteristics																															
<p>Colour As per color card Finish Semi Gloss Solid contents (% by volume) 45 ± 2 % Specific Gravity 1.40- 1.50 Recommended dry Film Thickness 30 microns Theoretical Coverage: 15 m²/ltr Flash Point: Non flammable</p> <p>Properties tested as per international Standards</p> <p>Viscosity ASTM D 562 Specific Gravity ASTM D 1475 Gloss ASTM D 523</p>																															
Packing Size	Storage & Handling																														
<p>1 USG and 18 Liters. Packing may vary from country to country according to local requirements. Also available in bases for instant color mixing at point of sale through Sherwin Williams automatic dispensing system.</p>	<p>Product must be stored in accordance to national regulations. The product should be kept in well ventilated place protected from heat and direct sunlight. The containers must be kept tightly closed.</p>																														



**SHERWIN
WILLIAMS.**

SherLux Harmony Semi Gloss

Safety Precautions	Application Procedures
<p>Material health and safety data sheet is available upon request. Please observe the precautionary notice displayed on the container. Ensure proper ventilation during application and drying of paint. Avoid inhalation of paint mist and vapors and skin contact. Spillage of paint on skin should immediately be removed with suitable cleanser soap and water. Eyes should be well flushed with water and immediate medical attention should be sought.</p>	<p><u>Surface Preparation:</u> The surface should be properly primed ..</p> <p><u>Application Conditions:</u> Minimum temperature at 15° C and relative humidity 20 - 85%.</p> <p><u>Application Details:</u> Application method By airless , Brush or roller Thinning Fresh water (only when required) Paint is ready to use Recommended thinning For brush/ roller / Airless max. 5 to 10 %</p> <p><u>Guiding data for airless spray:</u> Nozzle orifice .015 " - .021 " Nozzle Pressure 150 BARS / 2100 psi</p>
Recommended Uses	Environmental Compliance
<p>Can be used on most surfaces i.e. plaster, stucco filler, gypsum board, concrete, asbestos, cement sheeting, rendered block work etc. This product is recommended for interior use only.</p>	<p>VOC Limits Complies to</p> <p>LEED EQ credit 4.2</p> <p>MPI</p> <p>Green Seal GS 11</p> <p>EPA</p> <p>VOC : 0 g/l</p>