



**SHERWIN  
WILLIAMS.**

# SherLast Exterior Putty

Description	System Recommendation																		
SherLast Exterior Putty is an Acrylic based putty which provides good base for subsequent coats with good filling and sanding properties.	<b>On old &amp; Porous Substrates:</b>																		
	SherLast Primer Sealer	One coat																	
	<b>SherLast Exterior Putty</b>	<b>1-2 coats to fill imperfections</b>																	
	Any recommended top coat	2 Coats																	
	<b>On new cured concrete, plastered and gypsum substrates:</b>																		
	SherLast AR Primer	1 coat																	
	<b>SherLast Exterior Putty</b>	<b>1-2 coats to fill imperfections</b>																	
	Any recommended top coat	2 Coats																	
	<b>Drying Time:</b> Typically at recommended film thickness , drying time is generally depend on good ventilation.																		
	<table border="1"> <thead> <tr> <th rowspan="2">Substrate Temp</th> <th rowspan="2">Dry to Touch</th> <th rowspan="2">Dry to Handle</th> <th colspan="2">Re-coating Interval</th> </tr> <tr> <th>Minimum</th> <th>Maximum</th> </tr> </thead> <tbody> <tr> <td>23° C</td> <td>30 mnts</td> <td>3 h</td> <td>2hr</td> <td></td> </tr> <tr> <td>35° C</td> <td>15 mnts</td> <td>2 h</td> <td>1hr</td> <td></td> </tr> </tbody> </table>	Substrate Temp	Dry to Touch	Dry to Handle	Re-coating Interval		Minimum	Maximum	23° C	30 mnts	3 h	2hr		35° C	15 mnts	2 h	1hr		
Substrate Temp	Dry to Touch				Dry to Handle	Re-coating Interval													
		Minimum	Maximum																
23° C	30 mnts	3 h	2hr																
35° C	15 mnts	2 h	1hr																
Characteristics																			
Colour	White																		
Finish	Flat																		
Solid contents (% by volume)	54 ± 2 %																		
Specific Gravity	1.65- 1.75																		
Recommendedry Film Thickness	100 microns Per Coat																		
Theoretical Coverage:	2 m <sup>2</sup> /Kg in one coat																		
Flash Point:	Non flammable																		
<b>Properties tested as per international Standards</b>																			
Viscosity	ASTM D 562																		
Specific Gravity	ASTM D 1475																		
Gloss	ASTM D 523																		
Packing Size	Storage & Handling																		
5 kgs and 25 kgs. Packing may vary from country to country according to local requirements.	Product must be stored in accordance to national regulations. The product should be kept in well ventilated place protected from heat and direct sunlight. The containers must be kept tightly closed.																		



# SherLast Exterior Putty

Safety Precautions	Application Procedures				
<p>Material health and safety data sheet is available upon request. Please observe the precautionary notice displayed on the container. Ensure proper ventilation during application and drying of paint. Avoid inhalation of paint mist and vapors and skin contact. Spillage of paint on skin should immediately be removed with suitable cleanser soap and water. Eyes should be well flushed with water and immediate medical attention should be sought.</p>	<p><b>Surface Preparation:</b> The surface should be properly primed . In case of chalky and difficult surfaces it should be primed with SherLast Primer Sealer.</p> <p><b>Application Conditions:</b> Minimum temperature at 15° C and relative humidity 20 - 85%.</p> <p><b>Application Details:</b></p> <table border="0"> <tr> <td>Application method</td> <td>Scrapper, Putty Knife</td> </tr> <tr> <td>Thinning</td> <td>Paint is ready to use</td> </tr> </table>	Application method	Scrapper, Putty Knife	Thinning	Paint is ready to use
Application method	Scrapper, Putty Knife				
Thinning	Paint is ready to use				
Recommended Uses	Environmental Compliance				
<p>Can be used on most surfaces i.e. plaster, wood, concrete, asbestos, cement sheeting, rendered block work etc. This product is recommended for Exterior use only.</p>	<p><b>VOC Limits Complies to</b></p> <p><b>LEED EQ credit 4.2</b></p> <p><b>MPI E3</b></p> <p><b>Green Seal GS 11</b></p> <p><b>EPA</b></p> <p><b>VOC &lt; 50g/l</b></p>				