



**SHERWIN
WILLIAMS.**

SherLast Primer Sealer

Description	System Recommendation																									
<p>SherLast Primer Sealer is a solvent based Acrylic primer which is having excellent sealing and penetrating properties which provides excellent adhesion on old and porous substrates. Ideal primer for interior and exterior substrates with good flow and leveling properties.</p>	<p>On old & Porous Substartes:</p> <table border="1"> <tr> <td>SherLast Primer Sealer</td> <td>One coat</td> </tr> <tr> <td>Any recommended top coat</td> <td>2 Coats</td> </tr> </table> <p>On new cured concrete, plastered and gypsum substrates:</p> <table border="1"> <tr> <td>SherLast Alkali Resistant Primer</td> <td>1 coat</td> </tr> <tr> <td>Any recommended top coat</td> <td>2 Coats</td> </tr> </table> <p>Drying Time: Typically at recommended film thickness , drying time is generally depend on good ventilation.</p> <table border="1"> <thead> <tr> <th rowspan="2">Substrate Temp</th> <th rowspan="2">Dry to Touch</th> <th rowspan="2">Dry to Handle</th> <th colspan="2">Re-coating Interval</th> </tr> <tr> <th>Minimum</th> <th>Maximum</th> </tr> </thead> <tbody> <tr> <td>23° C</td> <td>30 mnts</td> <td>3 h</td> <td>2hr</td> <td></td> </tr> <tr> <td>35° C</td> <td>15 mnts</td> <td>2 h</td> <td>1hr</td> <td></td> </tr> </tbody> </table>	SherLast Primer Sealer	One coat	Any recommended top coat	2 Coats	SherLast Alkali Resistant Primer	1 coat	Any recommended top coat	2 Coats	Substrate Temp	Dry to Touch	Dry to Handle	Re-coating Interval		Minimum	Maximum	23° C	30 mnts	3 h	2hr		35° C	15 mnts	2 h	1hr	
SherLast Primer Sealer	One coat																									
Any recommended top coat	2 Coats																									
SherLast Alkali Resistant Primer	1 coat																									
Any recommended top coat	2 Coats																									
Substrate Temp	Dry to Touch	Dry to Handle	Re-coating Interval																							
			Minimum	Maximum																						
23° C	30 mnts	3 h	2hr																							
35° C	15 mnts	2 h	1hr																							
Characteristics																										
<p>Colour White</p> <p>Finish Flat</p> <p>Solid contents (% by volume) 35 ± 2 %</p> <p>Specific Gravity 1.30- 1.40</p> <p>Recommended dry Film Thickness 30 microns</p> <p>Theoretical Coverage: 11.66 m²/ltr</p> <p>Flash Point: 40°C</p> <p>Properties tested as per international Standards</p> <p>Viscosity ASTM D 562</p> <p>Specific Gravity ASTM D 1475</p> <p>Gloss ASTM D 523</p>																										
Packing Size	Storage & Handling																									
<p>1 USG and 18 Liters. Packing may vary from country to country according to local requirements.</p>	<p>Product must be stored in accordance to national regulations. The product should be kept in well ventilated place protected from heat and direct sunlight. The containers must be kept tightly closed.</p>																									

