



**SHERWIN
WILLIAMS.**

SherLast Spray Plaster

Description	System Recommendation																		
<p>SherLast Spray Plaster is an Acrylic based texture which gives many different patterns of textures when it is applied by hopper gun/trowel at exterior substrates.</p>	<p>On old & Porous Substrates:</p> <table border="1"> <tr> <td>SherLast Primer Sealer</td> <td>One coat</td> </tr> <tr> <td>SherLast Spray Plaster</td> <td>1 Coat</td> </tr> <tr> <td>Any recommended top coat</td> <td>Two Coats</td> </tr> </table> <p>On new cured concrete, plastered and gypsum substrates:</p> <table border="1"> <tr> <td>SherLast Alkali Resistant Primer</td> <td>1 coat</td> </tr> <tr> <td>SherLast Spray Plaster</td> <td>1 Coat</td> </tr> <tr> <td>Any recommended top coat</td> <td>Two Coats</td> </tr> </table>		SherLast Primer Sealer	One coat	SherLast Spray Plaster	1 Coat	Any recommended top coat	Two Coats	SherLast Alkali Resistant Primer	1 coat	SherLast Spray Plaster	1 Coat	Any recommended top coat	Two Coats					
SherLast Primer Sealer	One coat																		
SherLast Spray Plaster	1 Coat																		
Any recommended top coat	Two Coats																		
SherLast Alkali Resistant Primer	1 coat																		
SherLast Spray Plaster	1 Coat																		
Any recommended top coat	Two Coats																		
Characteristics	<p>Drying Time: Typically at recommended film thickness , drying time is generally depend on good ventilation.</p> <table border="1"> <thead> <tr> <th rowspan="2">Substrate Temp</th> <th rowspan="2">Dry to Touch</th> <th rowspan="2">Dry to Handle</th> <th colspan="2">Re-coating Interval</th> </tr> <tr> <th>Minimum</th> <th>Maximum</th> </tr> </thead> <tbody> <tr> <td>23° C</td> <td>30 mnts</td> <td>3 h</td> <td>2hr</td> <td></td> </tr> <tr> <td>35° C</td> <td>15 mnts</td> <td>2 h</td> <td>1hr</td> <td></td> </tr> </tbody> </table>		Substrate Temp	Dry to Touch	Dry to Handle	Re-coating Interval		Minimum	Maximum	23° C	30 mnts	3 h	2hr		35° C	15 mnts	2 h	1hr	
Substrate Temp	Dry to Touch	Dry to Handle				Re-coating Interval													
			Minimum	Maximum															
23° C	30 mnts	3 h	2hr																
35° C	15 mnts	2 h	1hr																
<p>Colour As per color card Finish Flat Solid contents (% by volume) 65 ± 2 % Specific Gravity 1.68- 1.75 Recommended dry film Thickness 200 microns Theoretical Coverage*: 0.5 – 0.8 m²/kg Flash Point: Non flammable</p> <p>*The practical spreading rate of the product depends on the surface, application method, actual DFT and the wasted amount. It is recommended to check the practical coverage on site prior to full scale application.</p> <p>Properties tested as per international Standards Viscosity ASTM D 562 Specific Gravity ASTM D 1475 Gloss ASTM D 523</p>																			
Packing Size	Storage & Handling																		
<p>25 kgs. Packing may vary from country to country according to local requirements.</p>	<p>Product must be stored in accordance to national regulations. The product should be kept in well ventilated place protected from heat and direct sunlight. The containers must be kept tightly closed.</p>																		



**SHERWIN
WILLIAMS.**

SherLast Spray Plaster

Safety Precautions

Material health and safety data sheet is available upon request. Please observe the precautionary notice displayed on the container. Ensure proper ventilation during application and drying of paint. Avoid inhalation of paint mist and vapors and skin contact. Spillage of paint on skin should immediately be removed with suitable cleanser soap and water. Eyes should be well flushed with water and immediate medical attention should be sought.

Application Procedures

Surface Preparation:

The surface should be properly primed . In case of chalky and difficult surfaces it should be primed with SherLast Primer Sealer.

Application Conditions:

Minimum temperature at 15° C and relative humidity 20 - 85%.

Application Details:

Application method	Hopper Gun, Scraper.
Thinning	Paint is ready to use

Recommended Uses

Can be used on most exterior surfaces i.e. plaster, concrete, asbestos, cement sheeting, rendered block work etc.

Environmental Compliance

VOC Limits Complies to

LEED EQ credit 4.2

MPI E3

Green Seal GS 11

EPA

VOC < 50g/l