



**SHERWIN  
WILLIAMS.**

# SherLux Enamel Gloss

Description	System Recommendation																		
<p><b>SherLux Enamel Gloss</b> is a durable quality interior Alkyd paint which is having good hiding, whiteness, smooth finish and leveling properties.</p>	<p><b>On Steel/Metal Substaries:</b></p> <table border="1" data-bbox="764 590 1528 657"> <tr> <td>Anti Rust Red Oxide Metal Primer</td> <td>One coat</td> </tr> <tr> <td><b>Sherlux Enamel Gloss</b></td> <td><b>2 Coats</b></td> </tr> </table> <p><b>On new cured concrete, plastered and gypsum substrates:</b></p> <table border="1" data-bbox="764 758 1528 858"> <tr> <td>SherLux Primer</td> <td>1 coat</td> </tr> <tr> <td>SherLux Interior Putty</td> <td>1-2 coats to fill imperfections</td> </tr> <tr> <td><b>Sherlux Enamel Gloss</b></td> <td><b>2 Coats</b></td> </tr> </table>		Anti Rust Red Oxide Metal Primer	One coat	<b>Sherlux Enamel Gloss</b>	<b>2 Coats</b>	SherLux Primer	1 coat	SherLux Interior Putty	1-2 coats to fill imperfections	<b>Sherlux Enamel Gloss</b>	<b>2 Coats</b>							
Anti Rust Red Oxide Metal Primer	One coat																		
<b>Sherlux Enamel Gloss</b>	<b>2 Coats</b>																		
SherLux Primer	1 coat																		
SherLux Interior Putty	1-2 coats to fill imperfections																		
<b>Sherlux Enamel Gloss</b>	<b>2 Coats</b>																		
Characteristics	<p><b>Drying Time:</b> Typically at recommended film thickness , drying time is generally depend on good ventilation.</p>																		
<p><b>Colour</b> As per color card  <b>Finish</b> Gloss  <b>Solid contents (% by volume)</b> 40 ± 2 %  <b>Specific Gravity</b> 1.00- 1.10  <b>Recommended dry Film Thickness</b> 30 microns  <b>Theoretical Coverage:</b> 13.33 m<sup>2</sup>/ltr  <b>Flash Point:</b> 40°C</p>	<table border="1" data-bbox="764 1037 1528 1478"> <thead> <tr> <th rowspan="2">Substrate</th> <th rowspan="2">Dry to Touch</th> <th rowspan="2">Dry to Handle</th> <th colspan="2">Re-coating Interval</th> </tr> <tr> <th>Minimum</th> <th>Maximum</th> </tr> </thead> <tbody> <tr> <td>23° C</td> <td>2.5 hr</td> <td>24 hr</td> <td>4 hr</td> <td></td> </tr> <tr> <td>35° C</td> <td>2 hr</td> <td>20 hr</td> <td>3hr</td> <td></td> </tr> </tbody> </table>		Substrate	Dry to Touch	Dry to Handle	Re-coating Interval		Minimum	Maximum	23° C	2.5 hr	24 hr	4 hr		35° C	2 hr	20 hr	3hr	
Substrate	Dry to Touch	Dry to Handle				Re-coating Interval													
			Minimum	Maximum															
23° C	2.5 hr	24 hr	4 hr																
35° C	2 hr	20 hr	3hr																
<p>Properties tested as per international Standards</p>	<p><b>Storage &amp; Handling</b></p>																		
<p><b>Viscosity</b> ASTM D 4287  <b>Specific Gravity</b> ASTM D 1475  <b>Gloss</b> ASTM D 523</p>	<p>Product must be stored in accordance to national regulations. The product should be kept in well ventilated place protected from heat and direct sunlight. The containers must be kept tightly closed.</p>																		
Packing Size																			
<p>1 USG and 18 Liters. Packing may vary from country to country according to local requirements. Also available in bases for instant color mixing at point of sale through Sherwin Williams automatic dispensing system</p>																			



**SHERWIN  
WILLIAMS.**

# SherLux Enamel Gloss

Safety Precautions	Application Procedures								
<p>Material health and safety data sheet is available upon request. Please observe the precautionary notice displayed on the container. Ensure proper ventilation during application and drying of paint. Avoid inhalation of paint mist and vapors and skin contact. Spillage of paint on skin should immediately be removed with suitable cleanser soap and water. Eyes should be well flushed with water and immediate medical attention should be sought.</p>	<p><b><u>Surface Preparation:</u></b> The surface should be properly primed . In case of chalky and difficult surfaces it should be primed with SherLast Primer Sealer.</p> <p><b><u>Application Conditions:</u></b> Minimum temperature at 15° C and relative humidity 20 - 85%.</p> <p><b><u>Application Details:</u></b></p> <table><tr><td>Application method</td><td>By airless , Brush or roller</td></tr><tr><td>Thinning</td><td>Thinner YTF K-099 (only whenrequired)</td></tr></table> <p>Paint is ready to use Recommended thinning For brush/ roller / Airless max. 5 to 10 %</p> <p><b><u>Guiding data for airless spray:</u></b></p> <table><tr><td>Nozzle orifice</td><td>.015 " - .019 "</td></tr><tr><td>Nozzle Pressure</td><td>150 BARS / 2100 psi</td></tr></table>	Application method	By airless , Brush or roller	Thinning	Thinner YTF K-099 (only whenrequired)	Nozzle orifice	.015 " - .019 "	Nozzle Pressure	150 BARS / 2100 psi
Application method	By airless , Brush or roller								
Thinning	Thinner YTF K-099 (only whenrequired)								
Nozzle orifice	.015 " - .019 "								
Nozzle Pressure	150 BARS / 2100 psi								
<p><b>Recommended Uses</b></p> <p>Can be used on most surfaces i.e. steel, plaster, stucco filler, gypsum board, concrete, asbestos, cement sheeting, rendered block work etc. This product is recommended for interior use only.</p>	<p><b>Environmental Compliance</b></p> <p><b>Lead Free Paint</b></p>								