



**SHERWIN
WILLIAMS.**

SherLux Enamel Semi Gloss

Description	System Recommendation																																														
<p>SherLux Enamel Semi Gloss is a durable quality interior Alkyd paint which is having good hiding, whiteness, smooth finish and leveling properties.</p>	<p>On Steel/Metal Substrates:</p> <table border="1"> <tr> <td>Anti Rust Red Oxide Metal Primer</td> <td colspan="4">One coat</td> </tr> <tr> <td>Sherlux Enamel Semi Gloss</td> <td colspan="4">2 Coats</td> </tr> </table> <p>On new cured concrete, plastered and gypsum substrates:</p> <table border="1"> <tr> <td>SherLux Primer</td> <td colspan="4">1 coat</td> </tr> <tr> <td>SherLux Interior Putty</td> <td colspan="4">1-2 coats to fill imperfections</td> </tr> <tr> <td>Sherlux Enamel Semi Gloss</td> <td colspan="4">2 Coats</td> </tr> </table> <p>Drying Time: Typically at recommended film thickness , drying time is generally depend on good ventilation.</p> <table border="1"> <thead> <tr> <th rowspan="3">Substrate Temp</th> <th rowspan="3">Dry to Touch</th> <th rowspan="3">Dry to Handle</th> <th colspan="2">Re-coating Interval</th> </tr> <tr> <th>Minimum</th> <th>Maximum</th> </tr> </thead> <tbody> <tr> <td>23° C</td> <td>2.5 hr</td> <td>24 hr</td> <td>4 hr</td> <td></td> </tr> <tr> <td>35° C</td> <td>2 hr</td> <td>20 hr</td> <td>3hr</td> <td></td> </tr> </tbody> </table>					Anti Rust Red Oxide Metal Primer	One coat				Sherlux Enamel Semi Gloss	2 Coats				SherLux Primer	1 coat				SherLux Interior Putty	1-2 coats to fill imperfections				Sherlux Enamel Semi Gloss	2 Coats				Substrate Temp	Dry to Touch	Dry to Handle	Re-coating Interval		Minimum	Maximum	23° C	2.5 hr	24 hr	4 hr		35° C	2 hr	20 hr	3hr	
Anti Rust Red Oxide Metal Primer	One coat																																														
Sherlux Enamel Semi Gloss	2 Coats																																														
SherLux Primer	1 coat																																														
SherLux Interior Putty	1-2 coats to fill imperfections																																														
Sherlux Enamel Semi Gloss	2 Coats																																														
Substrate Temp	Dry to Touch	Dry to Handle	Re-coating Interval																																												
			Minimum	Maximum																																											
			23° C	2.5 hr	24 hr	4 hr																																									
35° C	2 hr	20 hr	3hr																																												
Characteristics																																															
<p>Colour As per color card</p> <p>Finish Semi Gloss</p> <p>Solid contents (% by volume) 41 ± 2 %</p> <p>Specific Gravity 1.00- 1.10</p> <p>Recommended dry Film Thickness 30 microns</p> <p>Theoretical Coverage: 13.66 m²/ltr</p> <p>Flash Point: 40°C</p> <p>Properties tested as per international Standards</p> <p>Viscosity ASTM D 4287</p> <p>Specific Gravity ASTM D 1475</p> <p>Gloss ASTM D 523</p>																																															
Packing Size	Storage & Handling																																														
<p>1 USG and 18 Liters. Packing may vary from country to country according to local requirements. Also available in bases for instant color mixing at point of sale through Sherwin Williams automatic dispensing system</p>	<p>Product must be stored in accordance to national regulations. The product should be kept in well ventilated place protected from heat and direct sunlight. The containers must be kept tightly closed.</p>																																														



**SHERWIN
WILLIAMS.**

SherLux Enamel Semi Gloss

Safety Precautions	Application Procedures								
<p>Material health and safety data sheet is available upon request. Please observe the precautionary notice displayed on the container. Ensure proper ventilation during application and drying of paint. Avoid inhalation of paint mist and vapors and skin contact. Spillage of paint on skin should immediately be removed with suitable cleanser soap and water. Eyes should be well flushed with water and immediate medical attention should be sought.</p>	<p><u>Surface Preparation:</u> The surface should be properly primed . In case of chalky and difficult surfaces it should be primed with SherLast Primer Sealer.</p> <p><u>Application Conditions:</u> Minimum temperature at 15° C and relative humidity 20 - 85%.</p> <p><u>Application Details:</u></p> <table><tr><td>Application method</td><td>By airless , Brush or roller</td></tr><tr><td>Thinning</td><td>Thinner YTF K-099 (only whenrequired)</td></tr></table> <p>Paint is ready to use Recommended thinning For brush/ roller / Airless max. 5 to 10 %</p> <p><u>Guiding data for airless spray:</u></p> <table><tr><td>Nozzle orifice</td><td>.015 " - .019 "</td></tr><tr><td>Nozzle Pressure</td><td>150 BARS / 2100 psi</td></tr></table>	Application method	By airless , Brush or roller	Thinning	Thinner YTF K-099 (only whenrequired)	Nozzle orifice	.015 " - .019 "	Nozzle Pressure	150 BARS / 2100 psi
Application method	By airless , Brush or roller								
Thinning	Thinner YTF K-099 (only whenrequired)								
Nozzle orifice	.015 " - .019 "								
Nozzle Pressure	150 BARS / 2100 psi								
<p>Recommended Uses</p> <p>Can be used on most surfaces i.e. steel, plaster, stucco filler, gypsum board, concrete, asbestos, cement sheeting, rendered block work etc. This product is recommended for interior use only.</p>	<p>Environmental Compliance</p> <p>Lead Free Paint</p>								