



**SHERWIN  
WILLIAMS.**

# SherLast Heritage Traditional Texture

Description	System Recommendation																																													
<p><b>Sherlast Heritage Traditional Texture</b> is a superior quality 100% Pure Acrylic flexible exterior paint specially designed to endure the extreme weather conditions of Middle East. The product has good flexibility, anti dust property, anti carbonation property and superb color retention against UV. Excellent resistance against Carbon Dioxide diffusion, Water vapor transmission and liquid water transmission</p>	<p><b>On old &amp; Porous Substrates:</b></p> <table border="1"> <tr> <td>SherLux Primer Sealer</td> <td>One coat</td> </tr> <tr> <td><b>Sherlast Heritage Traditional Texture</b></td> <td><b>1 Coat</b></td> </tr> </table> <p><b>On new cured concrete, plastered and gypsum substrates:</b></p> <table border="1"> <tr> <td>SherLast Alkali Resistant Primer</td> <td>1 coat</td> </tr> <tr> <td><b>Sherlast Heritage Traditional Texture</b></td> <td><b>1 Coat</b></td> </tr> </table> <p>Note: Number of coats depend on the application technique being used. Use SherLast Ultra Heritage Glaze Top Coat when special effects finish is required.</p> <p><b>Drying Time:</b> Typically at recommended film thickness , drying time is generally depend on good ventilation.</p>	SherLux Primer Sealer	One coat	<b>Sherlast Heritage Traditional Texture</b>	<b>1 Coat</b>	SherLast Alkali Resistant Primer	1 coat	<b>Sherlast Heritage Traditional Texture</b>	<b>1 Coat</b>																																					
SherLux Primer Sealer	One coat																																													
<b>Sherlast Heritage Traditional Texture</b>	<b>1 Coat</b>																																													
SherLast Alkali Resistant Primer	1 coat																																													
<b>Sherlast Heritage Traditional Texture</b>	<b>1 Coat</b>																																													
<table border="1"> <thead> <tr> <th colspan="2" style="background-color: #cccccc;">Characteristics</th> </tr> </thead> <tbody> <tr> <td><b>Colour</b></td> <td>As per color card</td> </tr> <tr> <td><b>Finish</b></td> <td>Silk</td> </tr> <tr> <td><b>Solid contents (% by volume)</b></td> <td>53 ± 2 %</td> </tr> <tr> <td><b>Specific Gravity</b></td> <td>1.45- 1.55</td> </tr> <tr> <td><b>Recommended dry Film Thickness</b></td> <td><b>150 – 800</b> microns</td> </tr> <tr> <td><b>Theoretical Coverage:</b></td> <td>0.4 - 0.64 m<sup>2</sup>/Kg</td> </tr> <tr> <td><b>Flash Point:</b></td> <td>Non flammable</td> </tr> <tr> <td><b>Crack bridging ability</b></td> <td>up to 1 mm</td> </tr> <tr> <td colspan="2">*The practical spreading rate of the product depends on the surface, application method, actual DFT and the wasted amount. It is recommended to check the practical coverage on site prior to full scale application.</td> </tr> <tr> <td colspan="2"><b>Properties tested as per international Standards</b></td> </tr> <tr> <td><b>Viscosity</b></td> <td><b>ASTM D 562</b></td> </tr> <tr> <td><b>Specific Gravity</b></td> <td><b>ASTM D 1475</b></td> </tr> <tr> <td><b>Gloss</b></td> <td><b>ASTM D 523</b></td> </tr> </tbody> </table>	Characteristics		<b>Colour</b>	As per color card	<b>Finish</b>	Silk	<b>Solid contents (% by volume)</b>	53 ± 2 %	<b>Specific Gravity</b>	1.45- 1.55	<b>Recommended dry Film Thickness</b>	<b>150 – 800</b> microns	<b>Theoretical Coverage:</b>	0.4 - 0.64 m <sup>2</sup> /Kg	<b>Flash Point:</b>	Non flammable	<b>Crack bridging ability</b>	up to 1 mm	*The practical spreading rate of the product depends on the surface, application method, actual DFT and the wasted amount. It is recommended to check the practical coverage on site prior to full scale application.		<b>Properties tested as per international Standards</b>		<b>Viscosity</b>	<b>ASTM D 562</b>	<b>Specific Gravity</b>	<b>ASTM D 1475</b>	<b>Gloss</b>	<b>ASTM D 523</b>	<table border="1"> <thead> <tr> <th rowspan="2" style="background-color: #cccccc;">Substrate Temp</th> <th rowspan="2" style="background-color: #cccccc;">Dry to Touch</th> <th rowspan="2" style="background-color: #cccccc;">Dry to Handle</th> <th colspan="2" style="background-color: #cccccc;">Re-coating Interval</th> </tr> <tr> <th style="background-color: #cccccc;">Minimum</th> <th style="background-color: #cccccc;">Maximum</th> </tr> </thead> <tbody> <tr> <td>23° C</td> <td>40 mnts</td> <td>3 h</td> <td>2hr</td> <td></td> </tr> <tr> <td>35° C</td> <td>20 mnts</td> <td>2 h</td> <td>1hr</td> <td></td> </tr> </tbody> </table>	Substrate Temp	Dry to Touch	Dry to Handle	Re-coating Interval		Minimum	Maximum	23° C	40 mnts	3 h	2hr		35° C	20 mnts	2 h	1hr	
Characteristics																																														
<b>Colour</b>	As per color card																																													
<b>Finish</b>	Silk																																													
<b>Solid contents (% by volume)</b>	53 ± 2 %																																													
<b>Specific Gravity</b>	1.45- 1.55																																													
<b>Recommended dry Film Thickness</b>	<b>150 – 800</b> microns																																													
<b>Theoretical Coverage:</b>	0.4 - 0.64 m <sup>2</sup> /Kg																																													
<b>Flash Point:</b>	Non flammable																																													
<b>Crack bridging ability</b>	up to 1 mm																																													
*The practical spreading rate of the product depends on the surface, application method, actual DFT and the wasted amount. It is recommended to check the practical coverage on site prior to full scale application.																																														
<b>Properties tested as per international Standards</b>																																														
<b>Viscosity</b>	<b>ASTM D 562</b>																																													
<b>Specific Gravity</b>	<b>ASTM D 1475</b>																																													
<b>Gloss</b>	<b>ASTM D 523</b>																																													
Substrate Temp	Dry to Touch	Dry to Handle	Re-coating Interval																																											
			Minimum	Maximum																																										
23° C	40 mnts	3 h	2hr																																											
35° C	20 mnts	2 h	1hr																																											
<table border="1"> <thead> <tr> <th style="background-color: #cccccc;">Packing Size</th> </tr> </thead> <tbody> <tr> <td>25 kgs. Packing may vary from country to country according to local requirements. Also available in bases for instant color mixing at point of sale through Sherwin Williams automatic dispensing system</td> </tr> </tbody> </table>	Packing Size	25 kgs. Packing may vary from country to country according to local requirements. Also available in bases for instant color mixing at point of sale through Sherwin Williams automatic dispensing system	<table border="1"> <thead> <tr> <th style="background-color: #cccccc;">Storage &amp; Handling</th> </tr> </thead> <tbody> <tr> <td>Product must be stored in accordance to national regulations. The product should be kept in well ventilated place protected from heat and direct sunlight. The containers must be kept tightly closed.</td> </tr> </tbody> </table>	Storage & Handling	Product must be stored in accordance to national regulations. The product should be kept in well ventilated place protected from heat and direct sunlight. The containers must be kept tightly closed.																																									
Packing Size																																														
25 kgs. Packing may vary from country to country according to local requirements. Also available in bases for instant color mixing at point of sale through Sherwin Williams automatic dispensing system																																														
Storage & Handling																																														
Product must be stored in accordance to national regulations. The product should be kept in well ventilated place protected from heat and direct sunlight. The containers must be kept tightly closed.																																														



**SHERWIN  
WILLIAMS.**

# SherLast Heritage Traditional Texture

Safety Precautions	Application Procedures								
<p>Material health and safety data sheet is available upon request. Please observe the precautionary notice displayed on the container. Ensure proper ventilation during application and drying of paint. Avoid inhalation of paint mist and vapors and skin contact. Spillage of paint on skin should immediately be removed with suitable cleanser soap and water. Eyes should be well flushed with water and immediate medical attention should be sought.</p>	<p><b><u>Surface Preparation:</u></b> The surface should be properly primed . In case of chalky and difficult surfaces it should be primed with SherLast Primer Sealer.</p> <p><b><u>Application Conditions:</u></b> Minimum temperature at 15° C and relative humidity 20 - 85%.</p> <p><b><u>Application Details:</u></b></p> <table><tr><td>Application method</td><td>By Trowel, Scrapper, Hopper Gun</td></tr><tr><td>Thinning</td><td>Fresh water (only when required) Paint is ready to use</td></tr></table> <p>Recommended thinning / Hopper Gun. Max 5 %</p> <p><b><u>Guiding data for Hopper gun spray:</u></b></p> <table><tr><td>Nozzle orifice</td><td>Small, Medium.</td></tr><tr><td>Nozzle Pressure</td><td>Maximum 100 BARS</td></tr></table>	Application method	By Trowel, Scrapper, Hopper Gun	Thinning	Fresh water (only when required) Paint is ready to use	Nozzle orifice	Small, Medium.	Nozzle Pressure	Maximum 100 BARS
Application method	By Trowel, Scrapper, Hopper Gun								
Thinning	Fresh water (only when required) Paint is ready to use								
Nozzle orifice	Small, Medium.								
Nozzle Pressure	Maximum 100 BARS								
Recommended Uses	Environmental Compliance								
<p>Can be used on exterior concrete, masonry, plaster and pre cast substrates where highly durable Heritage, Legacy finish is required .</p>	<p><b>VOC Limits Complies to</b></p> <p><b>LEED EQ credit 4.2</b></p> <p><b>MPI E3</b></p> <p><b>Green Seal GS 11</b></p> <p><b>EPA</b></p> <p><b>VOC &lt; 50g/l</b></p>								