



**SHERWIN
WILLIAMS.**

SherLast Texture Profile Medium

Description	System Recommendation																									
<p>SherLast Texture Profile Medium is an Acrylic based trowel applied texture rendering which gives many different highly durable and long lasting patterns with nice grooves effect when it is applied by trowel at exterior substrates. It has a capacity to hide hair line cracks upto 1mm</p>	<p>On old & Porous Substrates:</p> <table border="1"> <tr> <td>SherLast Primer Sealer</td> <td>One coat</td> </tr> <tr> <td>SherLast Texture Profile Medium</td> <td>1 Coat</td> </tr> </table> <p>On new cured concrete, plastered and gypsum substrates:</p> <table border="1"> <tr> <td>SherLast Alkali Resistant Primer</td> <td>1 coat</td> </tr> <tr> <td>SherLast Texture Profile Medium</td> <td>1 Coat</td> </tr> </table> <p>Drying Time: Typically at recommended film thickness , drying time is generally depend on good ventilation.</p> <table border="1"> <thead> <tr> <th rowspan="2">Substrate Temp</th> <th rowspan="2">Dry to Touch</th> <th rowspan="2">Dry to Handle</th> <th colspan="2">Re-coating Interval</th> </tr> <tr> <th>Minimum</th> <th>Maximum</th> </tr> </thead> <tbody> <tr> <td>23° C</td> <td>30 mnts</td> <td>3 h</td> <td>2hr</td> <td></td> </tr> <tr> <td>35° C</td> <td>15 mnts</td> <td>2 h</td> <td>1hr</td> <td></td> </tr> </tbody> </table>	SherLast Primer Sealer	One coat	SherLast Texture Profile Medium	1 Coat	SherLast Alkali Resistant Primer	1 coat	SherLast Texture Profile Medium	1 Coat	Substrate Temp	Dry to Touch	Dry to Handle	Re-coating Interval		Minimum	Maximum	23° C	30 mnts	3 h	2hr		35° C	15 mnts	2 h	1hr	
SherLast Primer Sealer	One coat																									
SherLast Texture Profile Medium	1 Coat																									
SherLast Alkali Resistant Primer	1 coat																									
SherLast Texture Profile Medium	1 Coat																									
Substrate Temp	Dry to Touch	Dry to Handle	Re-coating Interval																							
			Minimum	Maximum																						
23° C	30 mnts	3 h	2hr																							
35° C	15 mnts	2 h	1hr																							
Characteristics																										
<p>Colour As per color card Finish Flat Solid contents (% by volume) 67 ± 2 % Specific Gravity 1.70- 1.80 Recommended dry film Thickness 1000 to 2000 microns Theoretical Coverage*: 0.25 – 0.3 m²/kg Flash Point: Non flammable</p> <p>*The practical spreading rate of the product depends on the surface, application method, actual DFT and the wasted amount. It is recommended to check the practical coverage on site prior to full scale application.</p> <p>Properties tested as per international Standards Viscosity ASTM D 562 Specific Gravity ASTM D 1475 Gloss ASTM D 523</p>																										
Packing Size	Storage & Handling																									
<p>25 kgs. And 30 Kgs. Packing may vary from country to country according to local requirements.</p>	<p>Product must be stored in accordance to national regulations. The product should be kept in well ventilated place protected from heat and direct sunlight. The containers must be kept tightly closed.</p>																									



**SHERWIN
WILLIAMS.**

SherLast Texture Profile Medium

Safety Precautions	Application Procedures
<p>Material health and safety data sheet is available upon request. Please observe the precautionary notice displayed on the container. Ensure proper ventilation during application and drying of paint. Avoid inhalation of paint mist and vapors and skin contact. Spillage of paint on skin should immediately be removed with suitable cleanser soap and water. Eyes should be well flushed with water and immediate medical attention should be sought.</p>	<p>Surface Preparation: The surface should be properly primed . In case of chalky and difficult surfaces it should be primed with SherLast Primer Sealer.</p> <p>Application Conditions: Minimum temperature at 15° C and relative humidity 20 - 85%.</p> <p>Application Details: Application method by Trowel, Putty Knife & Hopper Gun Thinning Paint is ready to use</p>
Recommended Uses	Environmental Compliance
<p>Can be used on most exterior surfaces i.e. plaster, concrete, asbestos, cement sheeting, rendered block work etc.</p>	<p>VOC Limits Complies to</p> <p>LEED EQ credit 4.2</p> <p>MPI E3</p> <p>Green Seal GS 11</p> <p>EPA</p> <p>VOC < 50g/l</p>