



**SHERWIN
WILLIAMS.**

SherLast Ultra Heritage Atique Tex

Description	System Recommendation																																											
<p>SherLast Ultra Heritage Antique Tex is a superior quality 100% Pure Acrylic flexible exterior paint specially designed to endure the extreme weather conditions of Middle East. The product has good flexibility, anti dust property, anti carbonation property and superb color retention against UV. Excellent resistance against Carbon Dioxide diffusion, Water vapor transmission and liquid water transmission. This product cover minor cracks in concrete and plaster.</p>	<p>On old & Porous Substrates’:</p> <table border="1"> <tr> <td>SherLux Primer Sealer</td> <td></td> <td></td> <td></td> <td>One coat</td> </tr> <tr> <td>SherLast Ultra Heritage Antique Tex</td> <td></td> <td></td> <td></td> <td>1 Coat</td> </tr> </table> <p>On new cured concrete, plastered and gypsum substrates:</p> <table border="1"> <tr> <td>SherLast Alkali Resistant Primer</td> <td></td> <td></td> <td></td> <td>1 coat</td> </tr> <tr> <td>SherLast Ultra Heritage Antique Tex</td> <td></td> <td></td> <td></td> <td>1 Coat</td> </tr> </table> <p>Note: Number of coats depend on the application technique being used. Use SherLast Ultra Heritage Glaze Top Coat when special effects finish is required.</p> <p>Drying Time: Typically at recommended film thickness , drying time is generally depend on good ventilation.</p> <table border="1"> <thead> <tr> <th rowspan="2">Substrate</th> <th rowspan="2">Dry to Temp</th> <th rowspan="2">Dry to Touch</th> <th rowspan="2">Dry to Handle</th> <th colspan="2">Re-coating Interval</th> </tr> <tr> <th>Minimum</th> <th>Maximum</th> </tr> </thead> <tbody> <tr> <td></td> <td>23° C</td> <td>40 mnts</td> <td>3 h</td> <td>2hr</td> <td></td> </tr> <tr> <td></td> <td>35° C</td> <td>20 mnts</td> <td>2 h</td> <td>1hr</td> <td></td> </tr> </tbody> </table>				SherLux Primer Sealer				One coat	SherLast Ultra Heritage Antique Tex				1 Coat	SherLast Alkali Resistant Primer				1 coat	SherLast Ultra Heritage Antique Tex				1 Coat	Substrate	Dry to Temp	Dry to Touch	Dry to Handle	Re-coating Interval		Minimum	Maximum		23° C	40 mnts	3 h	2hr			35° C	20 mnts	2 h	1hr	
SherLux Primer Sealer				One coat																																								
SherLast Ultra Heritage Antique Tex				1 Coat																																								
SherLast Alkali Resistant Primer				1 coat																																								
SherLast Ultra Heritage Antique Tex				1 Coat																																								
Substrate	Dry to Temp	Dry to Touch	Dry to Handle	Re-coating Interval																																								
				Minimum	Maximum																																							
	23° C	40 mnts	3 h	2hr																																								
	35° C	20 mnts	2 h	1hr																																								
Characteristics																																												
Colour	As per color card																																											
Finish	Silk																																											
Solid contents (% by volume)	63 ± 2 %																																											
Specific Gravity	1.45- 1.55																																											
Recommended dry Film Thickness	150 – 800 microns																																											
Theoretical Coverage:	15 to 18 SQM per pail																																											
Flash Point:	Non flammable																																											
Crack bridging ability	up to 1 mm																																											
Properties tested as per international Standards																																												
Viscosity	ASTM D 562																																											
Specific Gravity	ASTM D 1475																																											
Gloss	ASTM D 523																																											
Packing Size	Storage & Handling																																											
25 kgs. Packing may vary from country to country according to local requirements. Also available in bases for instant color mixing at point of sale through Sherwin Williams automatic dispensing system	Product must be stored in accordance to national regulations. The product should be kept in well ventilated place protected from heat and direct sunlight. The containers must be kept tightly closed.																																											



**SHERWIN
WILLIAMS.**

SherLast Ultra Heritage Atique Tex

Safety Precautions	Application Procedures								
<p>Material health and safety data sheet is available upon request. Please observe the precautionary notice displayed on the container. Ensure proper ventilation during application and drying of paint. Avoid inhalation of paint mist and vapors and skin contact. Spillage of paint on skin should immediately be removed with suitable cleanser soap and water. Eyes should be well flushed with water and immediate medical attention should be sought.</p>	<p><u>Surface Preparation:</u> The surface should be properly primed . In case of chalky and difficult surfaces it should be primed with SherLast Primer Sealer.</p> <p><u>Application Conditions:</u> Minimum temperature at 15° C and relative humidity 20 - 85%.</p> <p><u>Application Details:</u></p> <table border="0"> <tr> <td>Application method</td> <td>By Trowel, Scrapper, Hopper Gun</td> </tr> <tr> <td>Thinning</td> <td>Fresh water (only when required) Paint is ready to use</td> </tr> </table> <p>Recommended thinning / Hopper Gun. Max 5 %</p> <p><u>Guiding data for Hopper gun spray:</u></p> <table border="0"> <tr> <td>Nozzle orifice</td> <td>Small, Medium.</td> </tr> <tr> <td>Nozzle Pressure</td> <td>Maximum 100 BARS</td> </tr> </table>	Application method	By Trowel, Scrapper, Hopper Gun	Thinning	Fresh water (only when required) Paint is ready to use	Nozzle orifice	Small, Medium.	Nozzle Pressure	Maximum 100 BARS
Application method	By Trowel, Scrapper, Hopper Gun								
Thinning	Fresh water (only when required) Paint is ready to use								
Nozzle orifice	Small, Medium.								
Nozzle Pressure	Maximum 100 BARS								
Recommended Uses	Environmental Compliance								
<p>Can be used on exterior concrete, masonry, plaster and pre cast substrates where highly durable Heritage, Legacy finish is required .</p>	<p>VOC Limits Complies to</p> <p>LEED EQ credit 4.2</p> <p>MPI E3</p> <p>Green Seal GS 11</p> <p>EPA</p> <p>VOC < 50g/l</p>								