



**SHERWIN
WILLIAMS.**

SherLast Ultra Silk

Description	System Recommendation																							
<p>SherLast Ultra Silk is a superior quality 100% Pure Acrylic exterior paint specially designed to endure the extreme weather conditions of Middle East. The product has excellent flexibility, anti dust property, anti carbonation property, superb color retention against UV and water repellency.</p>	<p>On old & Porous Substrates:</p> <table border="1"> <tr> <td>SherLux Primer Sealer</td> <td>One coat</td> </tr> <tr> <td>SherLast Ultra Silk</td> <td>2 Coats</td> </tr> </table> <p>On new cured concrete, plastered and gypsum substrates:</p> <table border="1"> <tr> <td>SherLast Alkali Resistant Primer</td> <td>1 coat</td> </tr> <tr> <td>SherLast Ultra Silk</td> <td>2 Coats</td> </tr> </table>	SherLux Primer Sealer	One coat	SherLast Ultra Silk	2 Coats	SherLast Alkali Resistant Primer	1 coat	SherLast Ultra Silk	2 Coats															
SherLux Primer Sealer	One coat																							
SherLast Ultra Silk	2 Coats																							
SherLast Alkali Resistant Primer	1 coat																							
SherLast Ultra Silk	2 Coats																							
Characteristics																								
<table> <tr> <td>Colour</td> <td>As per color card</td> </tr> <tr> <td>Finish</td> <td>Silk</td> </tr> <tr> <td>Solid contents (% by volume)</td> <td>39 ± 2 %</td> </tr> <tr> <td>Specific Gravity</td> <td>1.25- 1.35</td> </tr> <tr> <td>Recommended dry Film Thickness</td> <td>30 microns</td> </tr> <tr> <td>Theoretical Coverage:</td> <td>13 m²/ltr</td> </tr> <tr> <td>Flash Point:</td> <td>Non flammable</td> </tr> </table>	Colour	As per color card	Finish	Silk	Solid contents (% by volume)	39 ± 2 %	Specific Gravity	1.25- 1.35	Recommended dry Film Thickness	30 microns	Theoretical Coverage:	13 m ² /ltr	Flash Point:	Non flammable	<p>Drying Time: Typically at recommended film thickness , drying time is generally depend on good ventilation.</p>									
Colour	As per color card																							
Finish	Silk																							
Solid contents (% by volume)	39 ± 2 %																							
Specific Gravity	1.25- 1.35																							
Recommended dry Film Thickness	30 microns																							
Theoretical Coverage:	13 m ² /ltr																							
Flash Point:	Non flammable																							
<p>Properties tested as per international Standards</p> <table> <tr> <td>Viscosity</td> <td>ASTM D 562</td> </tr> <tr> <td>Specific Gravity</td> <td>ASTM D 1475</td> </tr> <tr> <td>Gloss</td> <td>ASTM D 523</td> </tr> </table>	Viscosity	ASTM D 562	Specific Gravity	ASTM D 1475	Gloss	ASTM D 523	<table border="1"> <thead> <tr> <th rowspan="2">Substrate</th> <th rowspan="2">Dry to Touch</th> <th rowspan="2">Dry to Handle</th> <th colspan="2">Re-coating Interval</th> </tr> <tr> <th>Minimum</th> <th>Maximum</th> </tr> </thead> <tbody> <tr> <td>23° C</td> <td>40 mnts</td> <td>3 h</td> <td>2hr</td> <td></td> </tr> <tr> <td>35° C</td> <td>20 mnts</td> <td>2 h</td> <td>1hr</td> <td></td> </tr> </tbody> </table>	Substrate	Dry to Touch	Dry to Handle	Re-coating Interval		Minimum	Maximum	23° C	40 mnts	3 h	2hr		35° C	20 mnts	2 h	1hr	
Viscosity	ASTM D 562																							
Specific Gravity	ASTM D 1475																							
Gloss	ASTM D 523																							
Substrate	Dry to Touch	Dry to Handle	Re-coating Interval																					
			Minimum	Maximum																				
23° C	40 mnts	3 h	2hr																					
35° C	20 mnts	2 h	1hr																					
Packing Size	Storage & Handling																							
<p>1 USG and 18 Liters. Packing may vary from country to country according to local requirements. Also available in bases for instant color mixing at point of sale through Sherwin Williams automatic dispensing system</p>	<p>Product must be stored in accordance to national regulations. The product should be kept in well ventilated place protected from heat and direct sunlight. The containers must be kept tightly closed.</p>																							



**SHERWIN
WILLIAMS.**

SherLast Ultra Silk

Safety Precautions	Application Procedures
<p>Material health and safety data sheet is available upon request. Please observe the precautionary notice displayed on the container. Ensure proper ventilation during application and drying of paint. Avoid inhalation of paint mist and vapors and skin contact. Spillage of paint on skin should immediately be removed with suitable cleanser soap and water. Eyes should be well flushed with water and immediate medical attention should be sought.</p>	<p><u>Surface Preparation:</u> The surface should be properly primed . In case of chalky and difficult surfaces it should be primed with SherLast Primer Sealer.</p> <p><u>Application Conditions:</u> Minimum temperature at 15° C and relative humidity 20 - 85%.</p> <p><u>Application Details:</u> Application method By airless , Brush or roller Thinning Fresh water (only when required) Paint is ready to use Recommended thinning For brush/ roller / Airless max. 5 to 10 %</p> <p><u>Guiding data for airless spray:</u> Nozzle orifice .015 " - .019 " Nozzle Pressure 150 BARS / 2100 psi</p>
Recommended Uses	Environmental Compliance
<p>Can be used on exterior concrete, masonry, plaster and pre cast substrates where extremely durable coating is required.</p>	<p>VOC Limits Complies to</p> <p>LEED EQ credit 4.2</p> <p>MPI E3</p> <p>Green Seal GS 11</p> <p>EPA</p> <p>VOC < 50g/l</p>