



**SHERWIN
WILLIAMS.**

SherLux Premium Gloss

Description	System Recommendation																																												
<p>SherLux Premiu Gloss is an excellent, durable quality interior Acrylic Gloss paint which is having excellent washability, flexibility, hiding, whiteness, luxury finish and leveling properties .Excellent adhesion to the substrate and wide range of vibrant colors. Complies to Saudi Arabian Standards (SASO) for interior paints.</p>	<p>On old & Porous Substartes:</p> <table border="1"> <tr> <td>SherLast Primer Sealer</td> <td colspan="3">One coat</td> </tr> <tr> <td>SherLux Interior Putty</td> <td colspan="3">1-2 coats to fill imperfections</td> </tr> <tr> <td>Sherlux Premium Gloss</td> <td colspan="3">2 Coats</td> </tr> </table> <p>On new cured concrete, plastered and gypsum substrates:</p> <table border="1"> <tr> <td>SherLux Premium Primer</td> <td colspan="3">1 coat</td> </tr> <tr> <td>SherLux Interior Putty</td> <td colspan="3">1-2 coats to fill imperfections</td> </tr> <tr> <td>Sherlux Premium Gloss</td> <td colspan="3">2 Coats</td> </tr> </table> <p>Drying Time: Typically at recommended film thickness , drying time is generally depend on good ventilation.</p> <table border="1"> <thead> <tr> <th rowspan="2">Substrate Temp</th> <th rowspan="2">Dry to Touch</th> <th rowspan="2">Dry to Handle</th> <th colspan="2">Re-coating Interval</th> </tr> <tr> <th>Minimum</th> <th>Maximum</th> </tr> </thead> <tbody> <tr> <td>23° C</td> <td>40 mnts</td> <td>3 h</td> <td>3hr</td> <td></td> </tr> <tr> <td>35° C</td> <td>20 mnts</td> <td>2 h</td> <td>1.5hr</td> <td></td> </tr> </tbody> </table>				SherLast Primer Sealer	One coat			SherLux Interior Putty	1-2 coats to fill imperfections			Sherlux Premium Gloss	2 Coats			SherLux Premium Primer	1 coat			SherLux Interior Putty	1-2 coats to fill imperfections			Sherlux Premium Gloss	2 Coats			Substrate Temp	Dry to Touch	Dry to Handle	Re-coating Interval		Minimum	Maximum	23° C	40 mnts	3 h	3hr		35° C	20 mnts	2 h	1.5hr	
SherLast Primer Sealer	One coat																																												
SherLux Interior Putty	1-2 coats to fill imperfections																																												
Sherlux Premium Gloss	2 Coats																																												
SherLux Premium Primer	1 coat																																												
SherLux Interior Putty	1-2 coats to fill imperfections																																												
Sherlux Premium Gloss	2 Coats																																												
Substrate Temp	Dry to Touch	Dry to Handle	Re-coating Interval																																										
			Minimum	Maximum																																									
23° C	40 mnts	3 h	3hr																																										
35° C	20 mnts	2 h	1.5hr																																										
Characteristics																																													
<p>Colour As per color card Finish Gloss Solid contents (% by volume) 38 ± 2 % Specific Gravity 1.15- 1.25 Recommended dry Film Thickness 30 microns Theoretical Coverage: 12.66 m²/ltr Flash Point: Non flammable</p> <p style="text-align: center;">Properties tested as per international Standards</p> <p>Viscosity ASTM D 562 Specific Gravity ASTM D 1475 Gloss ASTM D 523</p>																																													
Packing Size	Storage & Handling																																												
<p>1 USG and 18 Liters. Packing may vary from country to country according to local requirements. Also available in bases for instant color mixing at point of sale through Sherwin Williams automatic dispensing system.</p>	<p>Product must be stored in accordance to national regulations. The product should be kept in well ventilated place protected from heat and direct sunlight. The containers must be kept tightly closed.</p>																																												



**SHERWIN
WILLIAMS.**

SherLux Premium Gloss

Safety Precautions	Application Procedures								
<p>Material health and safety data sheet is available upon request. Please observe the precautionary notice displayed on the container. Ensure proper ventilation during application and drying of paint. Avoid inhalation of paint mist and vapors and skin contact. Spillage of paint on skin should immediately be removed with suitable cleanser soap and water. Eyes should be well flushed with water and immediate medical attention should be sought.</p>	<p><u>Surface Preparation:</u> The surface should be properly primed . In case of chalky and difficult surfaces it should be primed with SherLast Primer Sealer.</p> <p><u>Application Conditions:</u> Minimum temperature at 15° C and relative humidity 20 - 85%.</p> <p><u>Application Details:</u></p> <table><tr><td>Application method</td><td>By airless , Brush or roller</td></tr><tr><td>Thinning</td><td>Fresh water (only when required) Paint is ready to use</td></tr></table> <p>Recommended thinning For brush/ roller / Airless max. 5 to 10 %</p> <p><u>Guiding data for airless spray:</u></p> <table><tr><td>Nozzle orifice</td><td>.015 " - .019 "</td></tr><tr><td>Nozzle Pressure</td><td>150 BARS / 2100 psi</td></tr></table>	Application method	By airless , Brush or roller	Thinning	Fresh water (only when required) Paint is ready to use	Nozzle orifice	.015 " - .019 "	Nozzle Pressure	150 BARS / 2100 psi
Application method	By airless , Brush or roller								
Thinning	Fresh water (only when required) Paint is ready to use								
Nozzle orifice	.015 " - .019 "								
Nozzle Pressure	150 BARS / 2100 psi								
Recommended Uses	Environmental Compliance								
<p>Can be used on most surfaces i.e. plaster, stucco filler, gypsum board, concrete, asbestos, cement sheeting, rendered block work etc. This product is recommended for interior use only.</p>	<p>VOC Limits Complies to</p> <p>LEED EQ credit 4.2</p> <p>MPI E3</p> <p>Green Seal GS 11</p> <p>EPA</p> <p>VOC < 50g/l</p>								