



**SHERWIN
WILLIAMS.**

SherLux Premium Primer

Description	System Recommendation																				
<p>SherLux Premium Primer is a premium quality water based Acrylic emulsion primer which provide excellent base for subsequent coats with superb adhesion and penetrating properties. Excellent luxury primer for interior substrates with good flow and leveling properties.</p>	<p>On old & Porous Substaries:</p> <table border="1"> <tr> <td>SherLast Primer Sealer</td> <td colspan="2">One coat</td> </tr> <tr> <td>SherLux Interior Putty</td> <td colspan="2">1-2 coats to fill imperfections</td> </tr> <tr> <td>Any recommended top coat</td> <td colspan="2">2 Coats</td> </tr> </table> <p>On new cured concrete, plastered and gypsum substrates:</p> <table border="1"> <tr> <td>SherLux Premium Primer</td> <td colspan="2">1 coat</td> </tr> <tr> <td>SherLux Interior Putty</td> <td colspan="2">1-2 coats to fill imperfections</td> </tr> <tr> <td>Any recommended top coat</td> <td colspan="2">2 Coats</td> </tr> </table>			SherLast Primer Sealer	One coat		SherLux Interior Putty	1-2 coats to fill imperfections		Any recommended top coat	2 Coats		SherLux Premium Primer	1 coat		SherLux Interior Putty	1-2 coats to fill imperfections		Any recommended top coat	2 Coats	
SherLast Primer Sealer	One coat																				
SherLux Interior Putty	1-2 coats to fill imperfections																				
Any recommended top coat	2 Coats																				
SherLux Premium Primer	1 coat																				
SherLux Interior Putty	1-2 coats to fill imperfections																				
Any recommended top coat	2 Coats																				
Characteristics	<p>Drying Time: Typically at recommended film thickness , drying time is generally depend on good ventilation.</p> <table border="1"> <thead> <tr> <th rowspan="2">Substrate Temp</th> <th rowspan="2">Dry to Touch</th> <th rowspan="2">Dry to Handle</th> <th colspan="2">Re-coating Interval</th> </tr> <tr> <th>Minimum</th> <th>Maximum</th> </tr> </thead> <tbody> <tr> <td>23° C</td> <td>30 mnts</td> <td>3 h</td> <td>2hr</td> <td></td> </tr> <tr> <td>35° C</td> <td>15 mnts</td> <td>2 h</td> <td>1hr</td> <td></td> </tr> </tbody> </table>			Substrate Temp	Dry to Touch	Dry to Handle	Re-coating Interval		Minimum	Maximum	23° C	30 mnts	3 h	2hr		35° C	15 mnts	2 h	1hr		
Substrate Temp	Dry to Touch	Dry to Handle	Re-coating Interval																		
			Minimum	Maximum																	
23° C	30 mnts	3 h	2hr																		
35° C	15 mnts	2 h	1hr																		
<p>Colour White Finish Flat Solid contents (% by volume) 36 ± 2 % Specific Gravity 1.35- 1.45 Recommended dry Film Thickness 30 microns Theoretical Coverage: 12 m²/ltr Flash Point: Non flammable</p> <p>Properties tested as per international Standards</p> <p>Viscosity ASTM D 562 Specific Gravity ASTM D 1475 Gloss ASTM D 523</p>																					
Packing Size	Storage & Handling																				
<p>1 USG and 18 Liters. Packing may vary from country to country according to local requirements.</p>	<p>Product must be stored in accordance to national regulations. The product should be kept in well ventilated place protected from heat and direct sunlight. The containers must be kept tightly closed.</p>																				



**SHERWIN
WILLIAMS.**

SherLux Premium Primer

Safety Precautions	Application Procedures								
<p>Material health and safety data sheet is available upon request. Please observe the precautionary notice displayed on the container. Ensure proper ventilation during application and drying of paint. Avoid inhalation of paint mist and vapors and skin contact. Spillage of paint on skin should immediately be removed with suitable cleanser soap and water. Eyes should be well flushed with water and immediate medical attention should be sought.</p>	<p><u>Surface Preparation:</u> The surface should be properly primed . In case of chalky and difficult surfaces it should be primed with SherLast Primer Sealer.</p> <p><u>Application Conditions:</u> Minimum temperature at 15° C and relative humidity 20 - 85%.</p> <p><u>Application Details:</u></p> <table><tr><td>Application method</td><td>By airless , Brush or roller</td></tr><tr><td>Thinning</td><td>Fresh water (only when required) Paint is ready to use</td></tr></table> <p>Recommended thinning For brush/ roller / Airless max. 5 to 10 %</p> <p><u>Guiding data for airless spray:</u></p> <table><tr><td>Nozzle orifice</td><td>.015 " - .019 "</td></tr><tr><td>Nozzle Pressure</td><td>150 BARS / 2100 psi</td></tr></table>	Application method	By airless , Brush or roller	Thinning	Fresh water (only when required) Paint is ready to use	Nozzle orifice	.015 " - .019 "	Nozzle Pressure	150 BARS / 2100 psi
Application method	By airless , Brush or roller								
Thinning	Fresh water (only when required) Paint is ready to use								
Nozzle orifice	.015 " - .019 "								
Nozzle Pressure	150 BARS / 2100 psi								
Recommended Uses	Environmental Compliance								
<p>Can be used on most surfaces i.e. plaster, stucco filler, gypsum board, concrete, asbestos, cement sheeting, rendered block work etc. This product is recommended for interior use only.</p>	<p>VOC Limits Complies to</p> <p>LEED EQ credit 4.2</p> <p>MPI E3</p> <p>Green Seal GS 11</p> <p>EPA</p> <p>VOC < 50g/l</p>								