



**SHERWIN  
WILLIAMS.**

# SherLux Premium Semi Gloss

Description	System Recommendation																																					
<p><b>SherLux Premium Semi Gloss</b> is an excellent, durable quality interior Acrylic Semi Gloss paint which is having excellent washability, flexibility, hiding, whiteness, luxury finish and leveling properties .Excellent adhesion to the substrate and wide range of vibrant colors. Complies to Saudi Arabian Standards (SASO) for interior paints.</p>	<p><b>On old &amp; Porous Substartes:</b></p> <table border="1"> <tr> <td>SherLast Primer Sealer</td> <td colspan="2">One coat</td> </tr> <tr> <td>SherLux Interior Putty</td> <td colspan="2">1-2 coats to fill imperfections</td> </tr> <tr> <td><b>Sherlux Premium Semi Gloss</b></td> <td colspan="2"><b>2 Coats</b></td> </tr> </table> <p><b>On new cured concrete, plastered and gypsum substrates:</b></p> <table border="1"> <tr> <td>SherLux Premium Primer</td> <td colspan="2">1 coat</td> </tr> <tr> <td>SherLux Interior Putty</td> <td colspan="2">1-2 coats to fill imperfections</td> </tr> <tr> <td><b>Sherlux Premium Semi Gloss</b></td> <td colspan="2"><b>2 Coats</b></td> </tr> </table> <p><b>Drying Time:</b> Typically at recommended film thickness , drying time is generally depend on good ventilation.</p> <table border="1"> <thead> <tr> <th rowspan="2">Substrate Temp</th> <th rowspan="2">Dry to Touch</th> <th rowspan="2">Dry to Handle</th> <th colspan="2">Re-coating Interval</th> </tr> <tr> <th>Minimum</th> <th>Maximum</th> </tr> </thead> <tbody> <tr> <td>23° C</td> <td>40 mnts</td> <td>3 h</td> <td>3hr</td> <td></td> </tr> <tr> <td>35° C</td> <td>20 mnts</td> <td>2 h</td> <td>1.5hr</td> <td></td> </tr> </tbody> </table>			SherLast Primer Sealer	One coat		SherLux Interior Putty	1-2 coats to fill imperfections		<b>Sherlux Premium Semi Gloss</b>	<b>2 Coats</b>		SherLux Premium Primer	1 coat		SherLux Interior Putty	1-2 coats to fill imperfections		<b>Sherlux Premium Semi Gloss</b>	<b>2 Coats</b>		Substrate Temp	Dry to Touch	Dry to Handle	Re-coating Interval		Minimum	Maximum	23° C	40 mnts	3 h	3hr		35° C	20 mnts	2 h	1.5hr	
SherLast Primer Sealer	One coat																																					
SherLux Interior Putty	1-2 coats to fill imperfections																																					
<b>Sherlux Premium Semi Gloss</b>	<b>2 Coats</b>																																					
SherLux Premium Primer	1 coat																																					
SherLux Interior Putty	1-2 coats to fill imperfections																																					
<b>Sherlux Premium Semi Gloss</b>	<b>2 Coats</b>																																					
Substrate Temp	Dry to Touch	Dry to Handle	Re-coating Interval																																			
			Minimum	Maximum																																		
23° C	40 mnts	3 h	3hr																																			
35° C	20 mnts	2 h	1.5hr																																			
Characteristics																																						
<p><b>Colour</b> As per color card  <b>Finish</b> Semi Gloss  <b>Solid contents (% by volume)</b> 45 ± 2 %  <b>Specific Gravity</b> 1.20- 1.30  <b>Recommended dry Film Thickness</b> 30 microns  <b>Theoretical Coverage:</b> 15 m<sup>2</sup>/ltr  <b>Flash Point:</b> Non flammable</p> <p style="text-align: center;"><b>Properties tested as per international Standards</b></p> <p><b>Viscosity</b> ASTM D 562  <b>Specific Gravity</b> ASTM D 1475  <b>Gloss</b> ASTM D 523</p>																																						
Packing Size	Storage & Handling																																					
<p>1 USG and 18 Liters. Packing may vary from country to country according to local requirements. Also available in bases for instant color mixing at point of sale through Sherwin Williams automatic dispensing system.</p>	<p>Product must be stored in accordance to national regulations. The product should be kept in well ventilated place protected from heat and direct sunlight. The containers must be kept tightly closed.</p>																																					



**SHERWIN  
WILLIAMS.**

# SherLux Premium Semi Gloss

Safety Precautions	Application Procedures										
<p>Material health and safety data sheet is available upon request. Please observe the precautionary notice displayed on the container. Ensure proper ventilation during application and drying of paint. Avoid inhalation of paint mist and vapors and skin contact. Spillage of paint on skin should immediately be removed with suitable cleanser soap and water. Eyes should be well flushed with water and immediate medical attention should be sought.</p>	<p><b>Surface Preparation:</b> The surface should be properly primed . In case of chalky and difficult surfaces it should be primed with SherLast Primer Sealer.</p> <p><b>Application Conditions:</b> Minimum temperature at 15° C and relative humidity 20 - 85%.</p> <p><b>Application Details:</b></p> <table border="0"> <tr> <td>Application method</td> <td>By airless , Brush or roller</td> </tr> <tr> <td>Thinning</td> <td>Fresh water (only when required) Paint is ready to use</td> </tr> <tr> <td>Recommended thinning For brush/ roller / Airless max.</td> <td>5 to 10 %</td> </tr> </table> <p><b>Guiding data for airless spray:</b></p> <table border="0"> <tr> <td>Nozzle orifice</td> <td>.015 " - .019 "</td> </tr> <tr> <td>Nozzle Pressure</td> <td>150 BARS / 2100 psi</td> </tr> </table>	Application method	By airless , Brush or roller	Thinning	Fresh water (only when required) Paint is ready to use	Recommended thinning For brush/ roller / Airless max.	5 to 10 %	Nozzle orifice	.015 " - .019 "	Nozzle Pressure	150 BARS / 2100 psi
Application method	By airless , Brush or roller										
Thinning	Fresh water (only when required) Paint is ready to use										
Recommended thinning For brush/ roller / Airless max.	5 to 10 %										
Nozzle orifice	.015 " - .019 "										
Nozzle Pressure	150 BARS / 2100 psi										
Recommended Uses	Environmental Compliance										
<p>Can be used on most surfaces i.e. plaster, stucco filler, gypsum board, concrete, asbestos, cement sheeting, rendered block work etc. This product is recommended for interior use only.</p>	<p><b>VOC Limits Complies to</b></p> <p><b>LEED EQ credit 4.2</b></p> <p><b>MPI E3</b></p> <p><b>Green Seal GS 11</b></p> <p><b>EPA</b></p> <p><b>VOC &lt; 50g/l</b></p>										