



**SHERWIN
WILLIAMS.**

Non Slip Aggregates

Description	System Recommendation									
<p>Silica based non slip aggregates Coarse, Medium and Fine to be used under various systems Acrylic, Epoxy, Polyurethane and Alkyd systems.</p>	<p>Concrete Surface :</p> <p>Kem Epoxy Clear Primer/Sealer 1 Coat 50 Microns DFT</p> <p>Hi-Solids Catalyzed Epoxy 1 Coat 100 Microns DFT</p> <p>Non Slip Aggregate by Sprinkle 1.8 Kg per Sqm</p> <p>Hi-Solids Catalyzed Epoxy 1 Coat 100 Microns DFT</p>									
Characteristics	<p>Anti-Slip Compliance Rating</p> <p>Fine Aggregate comply to R 11</p> <p>Medium Aggregate comply R 12</p> <p>Coarse Aggregate comply R13</p>	<p>Particle Size</p> <p>100-200 Microns</p> <p>300-400 Microns</p> <p>800-1000 Microns</p>								
<table border="0"> <tr> <td>Colour</td> <td>Neutral</td> </tr> <tr> <td>Specific Gravity</td> <td>2.6 - 2.7</td> </tr> <tr> <td>Flash Point:</td> <td>Non Flammable</td> </tr> <tr> <td>Specific Gravity</td> <td>ASTM D 1475</td> </tr> </table>	Colour	Neutral	Specific Gravity	2.6 - 2.7	Flash Point:	Non Flammable	Specific Gravity	ASTM D 1475		
Colour	Neutral									
Specific Gravity	2.6 - 2.7									
Flash Point:	Non Flammable									
Specific Gravity	ASTM D 1475									
Packing Size	Storage & Handling									
<p>25 Kgs Packing may vary from country to country according to local requirements. Also available in bases for instant color mixing at point of sale through Sherwin Williams automatic dispensing system</p>	<p>Product must be stored in accordance to national regulations. The product should be kept in well ventilated place protected from heat and direct sunlight. The containers must be kept tightly closed.</p>									



**SHERWIN
WILLIAMS.**

Non Slip Aggregates

Safety Precautions	Application Procedures
<p>Material health and safety data sheet is available upon request. Please observe the precautionary notice displayed on the container. Ensure proper ventilation during application and drying of paint. Avoid inhalation of paint mist and vapors and skin contact. Spillage of paint on skin should immediately be removed with suitable cleanser soap and water. Eyes should be well flushed with water and immediate medical attention should be sought.</p>	<p><u>Surface Preparation:</u></p> <p>The surface should be made free from moisture if any before application of any paint. Test the surface for moisture-free.</p> <p><u>Application Conditions:</u></p> <p>Minimum temperature at 15° C and relative humidity 20 - 85%.</p>
<p>Recommended Uses</p> <p>Can be used under various top coats to obtain non slip appearance.</p>	<p>Environmental Compliance</p> <p>Lead Free Paint</p>